

# Armed Services Technical Information Age

# AD

# 19785


NOTICE: WHEN GOVERNMENT OR OTHER DRAWINGS, SPECIFICATIONS OR OTHER DATA ARE USED FOR ANY PURPOSE OTHER THAN IN CONNECTION WITH A DEFINITELY RELATED GOVERNMENT PROCUREMENT OPERATION, THE U. S. GOVERNMENT THEREBY INCURS NO RESPONSIBILITY, NOR ANY OBLIGATION WHATSOEVER; AND THE FACT THAT THE GOVERNMENT MAY HAVE FORMULATED, FURNISHED, OR IN ANY WAY SUPPLIED THE SAID DRAWINGS, SPECIFICATIONS, OR OTHER DATA IS NOT TO BE REGARDED BY IMPLICATION OR OTHERWISE AS IN ANY MANNER LICENSING THE HOLDER OR ANY OTHER PERSON OR CORPORATION, OR CONVEYING ANY RIGHTS OR PERMISSION TO MANUFACTURE OR SELL ANY PATENTED INVENTION THAT MAY IN ANY WAY BE RELATED THEREWITH.

Reproduced by  
**DOCUMENT SERVICE CENTER**  
KNOTT BUILDING, DAYTON, 2, OHIO

# UNCLASSIFIED

19 785

UNIVERSITY OF CALIFORNIA  
INSTITUTE OF ENGINEERING RESEARCH  
BERKELEY, CALIFORNIA



Discussion of Paper  
"CREEP BEHAVIOR OF EXTRUDED ELECTROLYTIC MAGNESIUM" by C. S. Roberts  
Journal of Metals, AIME, September 1953, pp. 1121-1126

Thirty First Technical Report

By

O. D. Sherby and R. E. Frenkel

22, N7-onr-295, Task Order II,  
SERIES NO. NR-031-048  
ISSUE NO. 31  
DATE October 15, 1953

Discussion of Paper  
"CREEP BEHAVIOR OF EXTRUDED ELECTROLYTIC MAGNESIUM" by C. S. Roberts  
Journal of Metals, AIME, September 1953, pp. 1121-1126

By  
O. D. Sherby<sup>(1)</sup> and R. E. Frenkel<sup>(1)</sup>

Thirty First Technical Technical Report, Series 22, Issue 31  
N7-onr-295, Task Order II, NR-031-048

October 15, 1953

(1) Research Engineer, Institute of Engineering Research, University  
of California, Berkeley, California.

Discussion of Paper  
"Creep Behavior of Extruded Electrolytic Magnesium" by C. S. Roberts  
Journal of Metals, AIME, September 1953, pp. 1121-1126

\* \* \* \* \*

We wish to congratulate Dr. Roberts on his interesting contribution to the literature on creep. Although Dr. Roberts' conclusions appear in part to be substantiated by his experimental results, alternative interpretations appear to be worthy of consideration.

1. Dr. Roberts suggests that primary and secondary stages of creep arise from two independent phenomena. This is in agreement with Andrade's original ideas<sup>(1)</sup> on transient and quasi-viscous (steady-state) creep. McLean's investigations on aluminum<sup>(2,3)</sup>, however, clearly reveal that the main processes of deformation, i.e. migration of dislocations and grain boundary shearing, occur during primary creep as well as during secondary creep. Therefore the transient and steady-state components of creep cannot be ascribed to migration of dislocations and grain boundary shearing respectively.

2. Dr. Roberts indicates that steady-state creep becomes predominant at high temperatures whereas transient creep is predominant at low temperatures. Other evidence<sup>(4,5)</sup>, however, strongly suggests that stress and not temperature is the important factor in determining the shape of the creep curve. In recent investigations<sup>(4,5)</sup> it has been shown that the creep strain,  $\epsilon$ , at high temperatures, can be correlated by means of the functional equation

$$\epsilon = f(\theta, \sigma) \quad (1)$$

where  $\sigma$  = creep stress and  $\theta = t e^{-\Delta H/RT}$  where  $t$  = time under stress,  $\Delta H$  = activation energy for creep,  $R$  = gas constant and  $T$  = absolute

temperature. Thus at a given stress  $\sigma$ , the creep strain-time curves at various temperatures can be correlated by means of the parameter  $\Theta$ . An example of this correlation for the creep of high purity magnesium under a constant load of 2500 psi, is reproduced in Fig. 1. It will be observed that the 401°F and 496°F tests superimpose well for all three stages of creep yielding an activation energy of 34,000 calories per mole. These data suggest that the temperature does not determine the shape the creep curve and that the separation of a creep curve into two distinct components, each of which have markedly different temperature dependence, is untenable.

3. We question the validity of drawing breaks in the isothermal curves of the stress-secondary creep rate plots in Roberts' Figs. 4 and 5. With the possible exception of the 600°F data curvilinear lines would appear equally justified. Furthermore, on the basis of equation (1), the stress-secondary creep rate data can be correlated by means of a single parameter  $\dot{\epsilon} e^{\Delta H/RT}$ , since as previously proven<sup>(4,5)</sup>

$$\sigma = F(\dot{\epsilon} e^{\Delta H/RT}) \quad (2)$$

where  $\sigma$  is the stress and  $\dot{\epsilon}$  is the secondary creep rate. This method of correlation was applied to the data reported in Roberts' Figs. 4 and 5. As shown in our Figs. 2 and 3 these data correlate very well assuming an activation energy of 31,000 calories per mole in good agreement with the 34,000 calories per mole value obtained in our Fig. 1. It will be observed that Roberts' datum point at 1000 psi, 300°F veers to the right of the main curve; this is possibly due to the fact that at this low stress the secondary stage was not yet reached for the duration of testing and consequently the rate was faster than the actual secondary creep rate.

4. Dr. Roberts' analyses on transient creep suggest an activation energy of 15,500 calories per mole. This was deduced by observing a




FIG. 1 CORRELATION OF CREEP STRAIN - TIME DATA FOR HIGH PURITY MAGNESIUM BY THE RELATION  $\epsilon = f(\theta)$  AT A STRESS OF 2500 PSI.




FIG. 2 CORRELATION OF STRESS - SECONDARY CREEP RATE DATA FOR  
PURE MAGNESIUM BY THE RELATION  $\sigma = f(\dot{\epsilon} e^{\Delta H/RT})$ .  
(DATA FROM ROBERTS' FIGS. 4 AND 5)




FIG. 3 CORRELATION OF STRESS- SECONDARY CREEP-  
RATE DATA FOR PURE MAGNESIUM BY THE RELATION  
 $\sigma = f(\dot{\epsilon} e^{\Delta H/RT})$ .  
(DATA FROM ROBERTS' FIGS. 4 AND 5)



straight line relationship between  $\beta$  (from the empirical relation  $\epsilon = \beta t^n$ ) and the reciprocal of the absolute temperature at a given stress. But  $\beta$  is simply the value of the creep strain at one hour; consequently, the strained states that are being compared by this procedure are different for each temperature and therefore the activation energies so obtained are fictitious. The results shown in our Fig. 1 reveal that the activation energy for transient creep is no different from the activation energy for secondary creep, which furthermore should equal the activation energy for self-diffusion<sup>(5)</sup>.

The  $\Delta H$  values during transient creep can also be obtained from Roberts' data. Interpolation of the data in Table I and Fig. 7 yields  $\beta = .084$  at 2500 psi and 500°F, which also represents the strain at 1 hour under these test conditions. In Roberts' Fig. 2 extrapolation of the 400°F, 2500 psi data to  $\epsilon = 0.084$  indicates that the time to reach this strain equals about 30 hours. Therefore, from equation (1)

$$\Delta H = \frac{R \ln \frac{t_1}{t_2}}{\frac{1}{T_1} - \frac{1}{T_2}} = \frac{4.6 \log \frac{30}{1}}{\frac{1}{477} - \frac{1}{533}} = 31,000 \text{ calories per mole.}$$

The same answer was also obtained in comparing the 400°F and 500°F data at 1000 psi. These results yield further evidence that the activation energy for the so-called transient creep is essentially equal to that for steady-state creep.

5. Dr. Roberts suggests that the transient stage of creep arises solely from intragranular processes of basal slip and subgrain formation, whereas steady-state creep results from a cyclic process of sliding and migration of grain boundaries. McLean's results<sup>(3)</sup> on the creep of aluminum during secondary creep however indicate that the contribution of grain boundary shearing was never greater than a few percent of the total

strain, the main contribution to creep being crystallographic slip. He also showed that the strain due to grain boundary shearing exhibited primary and secondary creep characteristics similar to those exhibited by the total creep strain. Furthermore, Chaudhuri, Grant and Norton<sup>(6)</sup> obtained extensive basal slip and subgrain formation at about 600 psi and 500°F for high purity magnesium throughout the whole creep curve.

6. It is surprising that the size of subgrains formed during creep of magnesium remains constant independent of all test conditions investigated. Recent investigations on aluminum by Servi, Norton and Grant<sup>(7)</sup> as well as by Sherby and Dorn<sup>(8)</sup> indicate that for a constant amount of deformation the size of subgrains depends solely on the stress level independent of temperature. At high stresses the subgrains were very fine and at low stresses very coarse.

ACKNOWLEDGMENTS

The discussion of C. S. Roberts' paper on magnesium was suggested by current investigations on the creep of aluminum sponsored by the Office of Naval Research. The high purity magnesium alloy was graciously supplied by the Dow Chemical Company, Midland, Michigan. The authors wish to thank Professor J. E. Dorn for his interest and guidance in this report.

# REFERENCES

1. E. N. da C. Andrade, "On the Viscous Flow in Metals and Allied Phenomena", Proceedings, Royal Society (London), vol. 84A, 1910, pp. 1-12.
2. D. McLean, "Creep Processes in Coarse-Grained Aluminum", vol. 80, 1951-1952, pp. 507-519.
3. D. McLean, "Grain Boundary Slip during Creep of Aluminum", vol. 81, 1952-1953, pp. 293-300.
4. O. D. Sherby and J. E. Dorn, "Creep Correlations in Alpha Solid Solutions of Aluminum", Journal of Metals, AIME, vol. 4, September 1952, pp. 959-964.
5. O. D. Sherby, R. L. Orr and J. E. Dorn, "Creep Correlations of Metals at Elevated Temperatures", Institute of Engineering Research Report, University of California, Berkeley, Series No. 22, Issue No. 25, March 1, 1953. To be published in Journal of Metals, AIME.
6. A. R. Chaudhuri, N. J. Grant and J. T. Norton, "Metallographic Observations of the Deformation of High Purity Magnesium in Creep at 500°F", Journal of Metals, AIME, May 1953, pp. 712-716.
7. I. S. Servi, J. T. Norton and N. J. Grant, "Some Observations of Subgrain Formation during Creep in High Purity Aluminum", Journal of Metals, AIME, September 1952, pp. 965-971.
8. O. D. Sherby and J. E. Dorn, "Some Observations on Correlations between the Creep Behavior and the Resulting Structures in Alpha Solid Solutions", Journal of Metals, AIME, vol. 5, February 1953, pp. 324-330.

# DISTRIBUTION LIST

## Report No.

Chief of Naval Research, Dept. of Navy, Washington, Attn: Code 423 . . . . .	1-2
Chief of Naval Research, Dept. of Navy, Washington, Attn: Code 421 . . . . .	3
ONR Branch Office, New York . . . . .	4
ONR Branch Office, Chicago . . . . .	5
ONR Branch, Pasadena . . . . .	6
ONR Branch, San Francisco . . . . .	7
Director, Naval Research Lab., Wash., Attn: Tech. Inf. Officer . . . . .	8-13
Director, Naval Research Lab., Wash., Attn: Dr. G. I. Irwin, Code 510 . . . . .	14
Director, Naval Research Lab., Wash., Attn: Code 3500, Metallurgy Div. . . . .	15
Director, Naval Research Lab., Wash., Attn: Code 2020, Tech. Lib. . . . .	16
Director, Materials Lab. N.Y. Naval Shipyard, Attn: Code 907 . . . . .	17
Asst. Naval Attache for Research (London), New York . . . . .	18-23
Commanding Officer, Naval Air Mat. Ctr., Philadelphia, Aero. Mat. Lab. . . . .	24
Commanding Officer, U.S. Naval Ord. Test Sta. Inyokern, Calif. . . . .	25
Commanding Officer, U.S. Ord. Lab., White Oaks, Md. . . . .	26
Commanding Officer, Nav. Proving Grd., Dahlgren, Va., Attn: Lab. Div. . . . .	27
Commanding Officer and Director, David Taylor Model Basin, Wash. . . . .	28
Superintendent, Naval Gun Factory, Wash., Attn: Eng. Res. & Eval. Div., 720 . . . . .	29
Bureau of Aeronautics, Dept. of Navy, Wash., Dr. N.E. Promisel, AE-41 . . . . .	30-32
Bureau of Aeronautics, Dept. of Navy, Wash., Attn: Tech. Lib. . . . .	33
Bureau of Ordnance, Dept. of Navy, Wash., Attn: ReX . . . . .	34-36
Bureau of Ordnance, Dept. of Navy, Wash., Attn: Tech. Lib. Ad3 . . . . .	37
Bureau of Ordnance, Chief, Dept. of Navy, Wash., Attn: Re3a . . . . .	38
Bureau of Ships, Dept. of Navy, Wash., Attn: Code 343 . . . . .	39-41
Bureau of Ships, Dept. of Navy, Wash., Attn: Code 337L, Tech. Lib. . . . .	42
Bureau of Yards & Docks, Dept. of Navy, Wash., Res. & Stands. Div. . . . .	43
U.S. Naval Academy, Post Grad. School, Monterey, Calif., Metall. Dept. . . . .	44
U.S. Naval Engineering Expt. Station, Annapolis, Attn: Metals Lab. . . . .	45
Chief of Staff, U.S. Army, Wash., Attn: Div. of Res. & Development . . . . .	46
Office of Chief of Engineers, Dept. of Army, Wash., Res. & Develop. Bd. . . . .	47
Office of Chief of Ordnance, Dept. of the Army, Wash., Attn: ORDTB . . . . .	48-50
Commanding Officer, Watertown Arsenal, Mass., Attn: Lab. Div. . . . .	51
Commanding General, Wright Air Develop. Ctr., Dayton, Mat. Lab. (WCRT) . . . . .	52-53
Wright Air Develop. Ctr., Dayton, Attn: Metall. Grp. (WCRRL) . . . . .	54
U.S. Air Forces, Washington, Attn: Res. & Develop. Div. . . . .	55
Frankford Arsenal, Philadelphia, Attn: Dr. Harold Markus . . . . .	56
Office of Ordnance Res., Duke University, Durham, N.C., Dr. A.G. Guy . . . . .	57
Armed Services Tech. Inf. Agency, Dayton . . . . .	58-62
Office of Technical Services, Washington . . . . .	63
U.S.A.E.C. Div. of Research, Wash., Attn: Metall. Branch . . . . .	64
U.S.A.E.C. Div. of Research, Wash., Attn: Dr. D. W. Lillie . . . . .	65
U.S.A.E.C. Washington, Attn: B.M. Fry . . . . .	66-67
U.S.A.E.C. Mound Lab., Miamisburg, Ohio, Attn: Dr. J.J. Burbage . . . . .	68
U.S.A.E.C. N.Y. Operations Office, N.Y., Attn: Div. of Tech. Inf. . . . .	69
U.S.A.E.C. Library Branch, Oak Ridge, Tenn. . . . .	70
Argonne National Lab., Chicago, Attn: Dr. Hoylande D. Young . . . . .	71
Brookhaven National Lab., Upton, N.Y., Attn: Res. Library . . . . .	72
Carbide & Carbon Chem. Div., Oak Ridge, Central Files (K-25) . . . . .	73
Carbide & Carbon Chem. Div., Oak Ridge, Central Files & Inf. Off. (Y-12) . . . . .	74
General Electric Co., Richland, Washington, Attn: Miss M.G. Freidank . . . . .	75
Knolls Atomic Power Lab., Schenectady, Attn: Document Librarian . . . . .	76

# DISTRIBUTION LIST

## Report No.

Los Alamos Scientific Lab., Los Alamos, N. M., Attn: Document Custodian . .	77
North American Aviation, Downey, Calif. Attn: Dr. T. A. Coultas . . . . .	78
Oak Ridge Nat. Lab., Oak Ridge, Attn: Dr. J. H. Frye, Jr. . . . .	79
Oak Ridge Nat. Lab., Oak Ridge, Attn: Central Files . . . . .	80
Sandia Corporation, Albuquerque, New Mexico, Attn: Mr. Dale M. Evans . . .	81
University of Calif., Berkeley, Radiation Lab., Attn: Dr. R.K. Wakerling .	82
Mycalex Corp. of American, Attn: Mr. R. P. Wallace . . . . .	83
Westinghouse Elec. Co. Atomic Power Div., Pittsburgh, Attn: Librarian . . .	84
National Advisory Committee for Aeronautics, Washington . . . . .	85
National Bureau of Standards, Wash., Attn: Phys. Metall. Div. . . . .	86
National Bureau of Standards, Wash., Attn: Tech. Lib. . . . .	87
National Research Council, Wash., Attn: Dr. Finn Jonassen . . . . .	88
Research & Development Board, Wash., Attn: Metall. Panel . . . . .	89
Australian Embassy, Sci. Res. Liaison Office, Washington . . . . .	90
Armour Research Foundation, Chicago, Attn: Dr. W. E. Mahin . . . . .	91
Battelle Memorial Institute, Columbus, Attn: Dr. H. C. Cross . . . . .	92
General Electric Co., Schenectady, Attn: Dr. J. H. Holloman . . . . .	93
University of California, Dept. of Engineering, Berkeley . . . . .	94-108
Professor W. M. Baldwin, Jr., Case Institute of Technology, Cleveland . . .	109
Professor P. A. Beck, University of Illinois, Urbana, Ill. . . . .	110
Professor D. S. Clark, Calif. Institute of Tech., Pasadena, Calif. . . . .	111
Professor M. Cohen, Massachusetts Inst. of Technology, Boston . . . . .	112
Professor T. J. Dolan, University of Illinois, Urbana, Ill. . . . .	113
Professor Henry Eyring, University of Utah, Salt Lake City, Utah . . . . .	114
Professor N. J. Grant, Massachusetts Inst. of Technology, Boston . . . . .	115
Professor C. W. MacGregor, University of Pennsylvania, Philadelphia . . . .	116
Professor E. Machlin, Columbia University, New York City . . . . .	117
Professor Robert Maddin, Johns Hopkins, Baltimore, Md. . . . .	118
Professor R. F. Mehl, Carnegie Institute of Technology, Pittsburgh, Pa. . .	119
Professor N. M. Newmark, University of Illinois, Urbana, Ill. . . . .	120
Professor E. R. Parker, University of California, Berkeley . . . . .	121
Professor W. Prager, Brown University, Providence, R.I. . . . .	122
Professor George Sachs, Syracuse Univ., East Syracuse, N.Y. . . . .	123
Professor O. Cutler Shepard, Stanford University, Palo Alto, Calif. . . . .	124
Professor C. S. Smith, University of Chicago, Chicago . . . . .	125
Professor F. H. Spedding, Iowa State College, Ames, Iowa . . . . .	126
Professor S. Weissman, Rutgers University, New Brunswick, N. J. . . . .	127